

TECAMID 66 - Stock Shapes

Chemical Designation

PA 66 (Polyamide 66)

Colour

natural opaque

Density

1.15 g/cm³

Data generated directly after machining
(standard climate Germany).

Main features

- good slide and wear properties
- electrically insulating
- good wear properties
- high strength
- good weldable and bondable
- resistant to many oils, greases and fuels
- high toughness

Target Industries

- mechanical engineering
- conveyor technology
- packaging and paper machinery
- electrical engineering
- automotive industry
- textile industry
- precision engineering

Mechanical properties

parameter	value	unit	norm	comment
Modulus of elasticity (tensile test)	1mm/min	3500	MPa	DIN EN ISO 527-2 1) (1) For tensile test: specimen type 1b
Tensile strength	50mm/min	85	MPa	DIN EN ISO 527-2 (2) For flexural test: support span 64mm, norm specimen.
Tensile strength at yield	50mm/min	84	MPa	DIN EN ISO 527-2 (3) Specimen 10x10x10mm
Elongation at yield	50mm/min	7	%	DIN EN ISO 527-2 (4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
Elongation at break	50mm/min	70	%	DIN EN ISO 527-2 (5) For Charpy test: support span 64mm, norm specimen. n.b. = not broken
Flexural strength	2mm/min, 10 N	110	MPa	DIN EN ISO 178 2) (6) Specimen in 4mm thickness
Modulus of elasticity (flexural test)	2mm/min, 10 N	3100	MPa	DIN EN ISO 178 (1) For tensile test: specimen type 1b
Compression strength	1% / 2% 5mm/min, 10 N	20 / 35	MPa	EN ISO 604 3) (2) For flexural test: support span 64mm, norm specimen.
Compression modulus	5mm/min, 10 N	2700	MPa	EN ISO 604 4) (3) Specimen 10x10x10mm
Impact strength (Charpy)	max. 7,5J	n.b.	kJ/m ²	DIN EN ISO 179-1eU 5) (4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
Notched impact strength (Charpy)	max. 7,5J	5	kJ/m ²	DIN EN ISO 179-1ea (5) For Charpy test: support span 64mm, norm specimen. n.b. = not broken
Ball indentation hardness		175	MPa	ISO 2039-1 6) (6) Specimen in 4mm thickness

Thermal properties

parameter	value	unit	norm	comment
Glass transition temperature	47	°C	DIN 53765	1) (1) Found in public sources.
Melting temperature	258	°C	DIN 53765	(2) Found in public sources.
Service temperature short term	170	°C		Individual testing regarding application conditions is mandatory. 2)
Service temperature long term	100	°C		
Thermal expansion (CLTE)	23-60°C, long.	11	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2
Thermal expansion (CLTE)	23-100°C, long.	12	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2
Specific heat	1.5	J/(g*K)	ISO 22007-4:2008	
Thermal conductivity	0.36	W/(K*m)	ISO 22007-4:2008	

Electrical properties

parameter	value	unit	norm	comment
Surface resistance	10 ¹⁴	Ω	DIN IEC 60093	

Other properties

parameter	value	unit	norm	comment
Water absorption	24h / 96h (23°C)	0.2 / 0.4	%	DIN EN ISO 62 1) (1) Ø ca. 50mm, h=13mm (2) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Resistance to hot water/ bases	(+)			
Resistance to weathering	-			
Flammability (UL94)	corresponding to	HB	DIN IEC 60695-11-10;	2) (2) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensinger-online.com. Technical changes reserved.