

## TECAMID 6 GF 30 black

---

Chemical Designation:	Polyamide 6 ( Nylon 6 )
DIN Abbreviation:	PA 6 GF 30
Colour, Filler:	Black 30% glass fibres

---

TECAMID 66 GF 30 is a 30% glass fibre reinforced semi-crystalline engineering plastic with high strength and varied applications. (\*\* over 150 mm diameter 25% glass fibre content)

- Main characteristics:
- Very strong
  - Very rigid
  - UV resistant
  - Resistant to many oils, greases, diesel, petrol, cleaning fluids
  - Very abrasion resistant
  - Good heat distortion resistance
  - Not electrically insulating
  - Easily machined
  - Easily bonded
  - UV and weather resistant

Preferred fields: Mechanical engineering, automotive engineering, transport and conveyor technology, gears, couplings and engine construction, textile, packaging and paper processing machinery, precision engineering, agricultural machines

- Applications:
- Diverse machine parts
  - Levers
  - Thermal insulators
  - Wiper blades
  - Housing parts
  - Distance pieces
  - Friction rings
  - Support rings

---

Ensinger Ltd  
Wilfried Way  
Tonyrefail  
Mid Glam CF39 8JQ

Tel: 01443 678400  
Fax: 01443 675777  
Web: [www.ensinger.ltd.uk](http://www.ensinger.ltd.uk)  
Email: [sales@ensinger.ltd.uk](mailto:sales@ensinger.ltd.uk)

# TECAMID 6 GF 30 (black)

The following information corresponds with our current knowledge and indicates our products and possible applications. We cannot give a legally binding guarantee of certain properties or the suitability for a specific application. Existing commercial patents must be observed. A definitive quality guarantee is given in our general conditions of sales. Unless otherwise stated, these values represent averages taken from injection moulding samples. We reserve the right of technical alterations.

Properties	Unit	Test method DIN EN ISO / ASTM	Dry / Wet*
<b>Mechanical</b>			
Density	g/cm <sup>3</sup>	527 / D 792	1.35
Tensile strength at yield	MPa	527 / D 638	
Tensile strength at break	MPa	527 / D 638	140 / 110*
Elongation at break	%	527 / D 638	2.5 / 5 *
Modulus of elasticity in tension	MPa	527 / D 638	8500 / 6000*
Modulus of elasticity in flexure	MPa	178 / D 790	
Ball indentation hardness	MPa	2039 / 1	147
Impact strength	kJ/m <sup>2</sup>	179 / D 256	55
Creep rupture strength after 1000 hrs with static load	MPa		
Time yield limit for 1% elongation after 1000 hrs.	MPa		21 - 35
Coefficient of friction against hardened and ground steel p = 0,05 N/mm <sup>2</sup> , v = 0,6 m/s	-		0.46 - 0.52
Wear conditions as above	µm/km		
<b>Thermal</b>			
Crystalline melting point	°C	DIN 53 736	220
Glass transition temperature	°C	DIN 53 736	60 / 5*
Heat distortion temperature Method A Method B	°C °C	R 75 R 75	210 220

Properties	Unit	Test method DIN EN 150 / ASTM	Dry / Wet*
<b>Thermal</b>			
Max. service temperature short term long term	°C °C		180 100
Coefficient of thermal conductivity	W/(m · K)		0.28
Specific heat	J/(g · K)		1.5
Coefficient of thermal expansion	10 <sup>-5</sup> /K	DIN 53 483 / D 696	2-3
<b>Electrical</b>			
Dielectric constant at 10 <sup>5</sup> Hz		DIN 53 483	
Dielectric loss factor at 10 <sup>5</sup> Hz		DIN 53 483	
Specific volume resistance	Ω · cm	DIN 60093	9 x 10 <sup>13</sup>
Surface resistance	Ω	DIN 60093	5 x 10 <sup>13</sup>
Dielectric strength 1 mm	kV/mm	ASTM 149	
Tracking resistance		53 480	
<b>Miscellaneous</b>			
Moisture absorption: Equilibrium in standard atmosphere (23 °C / 50 % relative humidity)	%	62	2.1
Water absorption at saturation at 23 °C	%	62	6.6
Resistance to hot water, washing soda			limited resistant
Flammability according to UL standard 94			HB
Resistance to weathering			resistant

\* after storage in a standard 23/50 atmosphere (DIN 50 014) to equilibrium

ENSINGER: Production and stock programme

- Semi-finished product, finished parts, injection moulded parts and profiles in more than 500 materials and modifications.
- Engineering plastics: PA extruded or cast, POM, PC, PET, PBT, PPE, PP, PE
- High temperature plastics: PI, TPI, PEEK, PPS, PES, PPSU, PEI, PSU, PVDF, PCTFE, PTFE
- Stock length: Standard 3 metres. Cast rod and sheet 2 mts. Tube up to 3.5 mts. PE, PP, PVC, and PTFE 2 mts
- Pressed/sintered semi-finished product: PI, PEEK, PPS, PTFE/PI and modifications, as well as PCTFE in special sizes ie, large discs, tubes and rings with diameters up to about 1400 mm
- Material modifications: eg. glass, carbon and aramid fibre, talc, MoS<sub>2</sub>, graphite, PTFE, PE, silicone oil, internal lubrication