

## TECANAT natural - Stock Shapes

### Chemical Designation

PC (Polycarbonate)

### Colour

white transparent

### Density

1.19 g/cm<sup>3</sup>

### Main features

- high toughness
- electrically insulating
- good machinability
- easy to polish
- good heat deflection temperature
- sensitive to stress cracking
- good weldable and bondable

### Target Industries

- mechanical engineering
- medical technology
- electrical engineering
- construction industry
- food engineering
- conveyor technology
- automotive industry
- precision engineering
- home appliances

<b>Mechanical properties</b>	<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Modulus of elasticity (tensile test)	1mm/min	2200	MPa	DIN EN ISO 527-2	1) (1) For tensile test: specimen type 1b
Tensile strength	50mm/min	69	MPa	DIN EN ISO 527-2	(2) For flexural test: support span 64mm, norm specimen.
Tensile strength at yield	50mm/min	69	MPa	DIN EN ISO 527-2	(3) Specimen 10x10x10mm
Elongation at yield	50mm/min	6	%	DIN EN ISO 527-2	(4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
Elongation at break	50mm/min	90	%	DIN EN ISO 527-2	(5) For Charpy test: support span 64mm, norm specimen.
Flexural strength	2mm/min, 10 N	97	MPa	DIN EN ISO 178	2) n.b. = not broken
Modulus of elasticity (flexural test)	2mm/min, 10 N	2300	MPa	DIN EN ISO 178	(6) Specimen in 4mm thickness
Compression strength	1% / 2% 5mm/min, 10 N	16 / 29	MPa	EN ISO 604	3)
Compression modulus	5mm/min, 10 N	2000	MPa	EN ISO 604	4)
Impact strength (Charpy)	max. 7,5J	n.b.	kJ/m <sup>2</sup>	DIN EN ISO 179-1eU	5)
Notched impact strength (Charpy)	max. 7,5J	14	kJ/m <sup>2</sup>	DIN EN ISO 179-1eA	
Ball indentation hardness		128	MPa	ISO 2039-1	6)
<b>Thermal properties</b>	<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Glass transition temperature		149	°C	DIN 53765	1) (1) Found in public sources.
Melting temperature		n.a.	°C	DIN 53765	2) (2) n.a. = not applicable
Service temperature	short term	140	°C		3) (3) Found in public sources.
Service temperature	long term	120	°C		Individual testing regarding application conditions is mandatory.
Thermal expansion (CLTE)	23-60°C, long.	8	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	23-100°C, long.	8	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Specific heat		1.3	J/(g*K)	ISO 22007-4:2008	
Thermal conductivity		0.25	W/(K*m)	ISO 22007-4:2008	
<b>Electrical properties</b>	<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Specific surface resistance		10 <sup>14</sup>	Ω	DIN IEC 60093	
Specific volume resistance		10 <sup>14</sup>	Ω*cm	DIN IEC 60093	
<b>Other properties</b>	<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Water absorption	24h / 96h (23°C)	0.03 / 0.06	%	DIN EN ISO 62	1) (1) Ø ca. 50mm, h=13mm
Resistance to hot water/ bases		-	-	-	2) (2) - poor resistance
Resistance to weathering		(+)	-	-	3) (3) (+) limited resistance
Flammability (UL94)	listed (value at 0.4 and 1.5 mm)	HB		DIN IEC 60695-11-10;	

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensinger-online.com](http://www.ensinger-online.com). Technical changes reserved.